

## Technical data

		Xi 1 mm	Xi 2 mm	Xi 3 mm	Xi 4 mm	Xi 5 mm
Thickness	mm	1	2	3	4	5
Roll length	m	160	80	50	40	30
Roll width*	m	1	1	1	1	1
Resin uptake	kg/m <sup>2</sup>	0.6	1.2	1.8	2.4	3.0
Dry weight	g/m <sup>2</sup>	35	62	88	114	125
Density impregnated	kg/m <sup>3</sup>	630	630	630	630	630

\* Special widths on request

## Typical properties of Lantor Coremat® Xi impregnated with unsaturated polyester resin

Mechanical properties			Test method
Flexural strength	MPa	11	ASTM D790
Flexural modulus	MPa	1100	ASTM D790
Flatwise tensile strength	MPa	4	ASTM C297
Stress at 10% compression	MPa	10	ISO 844
Shear strength	MPa	5	ASTM C273-61
Shear modulus	MPa	35	ASTM C273-61

## Application of Lantor Coremat® Xi


Resin compatibility	Polyester Vinylester Epoxy
Processing method	Hand lay-up, spray-up

Keep Coremat® Xi away from direct sunlight. Store Lantor Coremat® in the original bag. This will ensure the proper working of the resin indicator. Please note that the resin indicator is not a guarantee that sufficient resin has been applied, but strictly a control mechanism to identify dry spots. Always check resin content.

The information contained in this document has been compiled in good faith by Lantor bv, but nevertheless no representation or warranty is given as to the accuracy or completeness of the (technical) information provided herein. Lantor bv can not be held liable for any damages arising from any (printing) errors or omissions in this information. Lantor bv reserves the right to make changes with respect to the information provided at any time without further notice.

Core material and print through barrier for hand lay-up and spray-up

- Resin Indicator
- Excellent impregnation
- Improved control



## For more information:

Lantor bv

Verlaat 22, P.O. Box 45

3900 AA Veenendaal

The Netherlands

Tel.: +31 (0)318 - 537 111

Fax.: +31 (0)318 - 537 420

E-mail: lantorbv@lantor.nl

Or visit our website: [www.lantor.nl](http://www.lantor.nl)